

Declaration of Performance

DECLARATION OF PERFORMANCE No **CIM0005** CPR **12th March 2024**

1. Unique identification code of the product type:

Rolled Lead Sheet to BSEN 12588: 2006

2. Type, batch or serial number or any other element allowing identification of the construction product as required under **Article 11 (4) of the CPR**:

Products are colour coded to denote their thickness (see item 8). Packaging will illustrate other production data.

3. Intended use or uses of the construction product in accordance with the application harmonised technical specification, as foreseen by the manufacturer:

Rolled Lead Sheet for Construction, Nuclear and Engineering.

4. Name, registration trade name or registered trade mark and contact address of the manufacturer as required under **Article 11 (5)**.

**Calder Industrial Materials Limited
Jupiter Drive
Chester West Employment Park
Chester, CH1 4EX**

5. Where applicable, name and contact address of the authorised representative whose mandate covers the tasks specified in **Article 12 (2)**.

**Roland Davies – Quality Manager
Calder Industrial Materials Limited
Jupiter Drive
Chester West Employment Park
Chester, CH1 4EX**

6. System or systems of assessment and verification of constancy of performance of the construction product as set out in **CPR, Annex V**:

System 2+

7. In case of the declaration of performance concerning a construction product covered by a harmonized standard:

**EN 14783: 2013 (see also BS EN 12588 2006)
Quality System to BS EN ISO 9001:2015
Certification conducted by BSI
Certificate number FM 702896**

8 Declared Performance

Essential Characteristics	Performance	Harmonised Technical Specification															
Water permeability	impermeable	EN 14783:2013															
Dimensional change	29,3 x 10 ⁻⁶ K ⁻¹																
Water vapour and air permeability	impermeable																
Appearance	Bluish grey soft metal																
Melting Temperature	327°c																
Fuming Temperature	500°c																
Boiling Point	1,750°c																
Density	11,34g/cm3																
Fire Rating	Lead roofs achieve the following ratings when tested to BS 476: Part 3. a) BA when laid on square edged boarding. b) AA when laid on T & G boarding or concrete;																
Reaction to Fire	Class A1 (CWFT)																
External Fire Performance	Class F _{roof}																
Odour	None																
Flash Point	No Performance Detected (NPD)																
Solubility in Water	Insoluble																
Chemical Composition	% by mass (m/m)																
Copper	0.03 to 0.06																
Antimony	max 0.005																
Bismuth	max 0.100																
Silver	max 0.005																
Tin	max 0.05																
Zinc	max 0.001																
Other impurities	max 0.005																
Lead	Remainder																
<table border="1"> <thead> <tr> <th>Nominal Thickness (mm)</th> <th>Colour</th> </tr> </thead> <tbody> <tr> <td>1.25 or 1.32</td> <td>green</td> </tr> <tr> <td>1.50 or 1.59</td> <td>yellow</td> </tr> <tr> <td>1.75 or 1.80</td> <td>blue</td> </tr> <tr> <td>2.00 or 2.24</td> <td>red</td> </tr> <tr> <td>2,50 or 2.65</td> <td>black</td> </tr> <tr> <td>3.00 or 3.15</td> <td>white</td> </tr> <tr> <td>3.50 or 3.55</td> <td>orange</td> </tr> </tbody> </table>	Nominal Thickness (mm)	Colour	1.25 or 1.32	green	1.50 or 1.59	yellow	1.75 or 1.80	blue	2.00 or 2.24	red	2,50 or 2.65	black	3.00 or 3.15	white	3.50 or 3.55	orange	Max deviation from the ordered nominal thickness, when measured shall be carried out on flat undamaged areas, at each end of the roll or split roll, at least 20mm away from the edge to avoid any burrs, physical marks and creases shall not exceed ± 5%.
Nominal Thickness (mm)	Colour																
1.25 or 1.32	green																
1.50 or 1.59	yellow																
1.75 or 1.80	blue																
2.00 or 2.24	red																
2,50 or 2.65	black																
3.00 or 3.15	white																
3.50 or 3.55	orange																
Width	The maximum deviation from the ordered nominal width shall not exceed ± 5mm.																
Length	The maximum deviation from the ordered nominal length shall not exceed +50mm.																



9 The performance of the product identified in points 1 and 2 is in conformity with the declared performance in points 8. This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 4.

Signed for and on behalf of the manufacturer by:

P. K. McKeon – Managing Director

.....
(Name and function)

Chester, 13th March 2024

.....
(place and date of issue)

A handwritten signature in black ink that reads "PKMcKeon" with a horizontal line underneath.

.....
(signature)